

## **FIRE TEST REPORT INFORMATION**

Classic Tredfx

**PBD106**

Aluminium Safety Stair Nosing for Carpet / Rubber Applications

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the [NCC 2019 and Fire Resistance of Floor Coverings](#).

### **Class 2 – 9 Properties of Floor Material and Coverings**

[Specification C1.10 of the NCC 2019](#) states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table 2; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification E1.5, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with Clause 6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the **Classic Tredfx PBD106** product, the fire test properties are:

- Critical Radiant Flux: 7.8 kW/m<sup>2</sup>
- Smoke Development Rate: 234 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our [Product Data Sheets](#) from the website.

*Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.*



**classic**  
architectural group

**For Every Step**

## AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O. Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

### TEST REPORT

CLIENT : CLASSIC ARCHITECTURAL PRODUCTS  
PTY LTD  
6 BEAUFORT STREET  
PRESTON VIC 3072

TEST NUMBER : 7-579085-CV  
ISSUE DATE : 10/06/2011  
PRINT DATE : 10/06/2011

SAMPLE DESCRIPTION Clients Ref: "Stair Tread Nosing"  
PVC strips affixed to cement sheet  
Approx total thickness: 9.5mm  
End Use: Stair Nosing

Material Specification:  
Nominal composition: PVC cement sheet  
Nominal mass: 3.5kg/m<sup>2</sup>

ASISO 9239.1-2003  
Part 1

Reaction to Fire Tests for Floorings  
Determination of the Burning Behaviour  
using a Radiant Heat Source

Date of sample arrival: 24/05/2011  
Date tested: 10/06/2011

Results:

CHF (Critical Heat Flux / Critical Radiant Flux)

|        | 1   | 2   | 3   | Mean |                   |
|--------|-----|-----|-----|------|-------------------|
| Length | 8.7 | 7.0 | 7.6 | 7.8  | kW/m <sup>2</sup> |
| Width  | 9.1 | -   | -   | -    | kW/m <sup>2</sup> |

Smoke Value

|        | 243 | 258 | 201 | 234 | % min |
|--------|-----|-----|-----|-----|-------|
| Length | 243 | 258 | 201 | 234 | % min |
| Width  | 254 | -   | -   | -   | % min |

Observations: transitory flaming, blistering, penetration of flame through to substrate

Note: Sample was conditioned in accordance with BS EN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing

Each specimen was clamped as supplied by client prior to testing

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use

188107 1

( END OF REPORT )

PAGE 1

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:  
-Chemical Testing of Textiles & Related Products  
-Mechanical Testing of Textiles & Related Products  
-Heat & Temperature Measurement

Accreditation No. 983  
Accreditation No. 985  
Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc (Hons)  
MANAGING DIRECTOR

020411/06

[www.classic-arch.com](http://www.classic-arch.com)