

For Every Step

FIRE TEST REPORT INFORMATION

Classic Integra
Shield 9100
Vinyl Scaper Matting

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the <u>NCC 2019 and Fire Resistance of Floor Coverings</u>.

Class 2 – 9 Properties of Floor Material and Coverings

Specification C1.10 of the NCC 2019 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table 2; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification E1.5, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with Clause 6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Integra Shield 9100 product, the fire test properties are:

- Critical Radiant Flux is 7.5 kW/m2
- Smoke Development Rate is 541 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our Product Data Sheets from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



For Every Step



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106 1st Floor, 191 Racecurse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

PTY LTD 6 BEAUFORT STR				TEST NUMBER : 7-574001-0 ISSUE DATE : 29/07/2010 PRINT DATE : 30/07/2010			
Color				0100 Scrap	er Entr	ance	
Material Specification Nominal composition: V. Nominal total mass: 83	inyl						
ASISO 9239.1-2003 Part 1	Determina	Reaction to Fire Tests for Floorings Determination of the Burning Behaviour using a Radiant Heat Source					
Date of sample arrival Date tested: Results:	28/07/201	22/06/2010 28/07/2010 CHF (Critical Heat Flux / Critical Radiant Flux) 1 2 3 Mean					
Length Width	8.0 8.2	7.1	7.5	7.5	kW/m2 kW/m2		
		Sm	oke Value			1981965	
Length Width	538 505	524	560	541	% min % min		
temperature of 23+/-2d 48 hours prior to test. Each specimen was clam cement board prior to	ing ped to a subst	REEL				1 01	
The test results relat- under the particular c sole criterion for ass	onditions of t	he test,	they are no	t intende	d to be	the	
182599 1			(END OF	REPORT	3	PAGE 1	
	NATA -Chemical Te Mechanical Te -Heat & Temp	sting of Textiles Testing of Textile perature Measure	y the National Asso & Related Products & & Related Product ment	ts I	Accreditatio Accreditatio Accreditation	n No. 983 n No. 985 1 No. 1356	
ic te te	his document is issued lentifying descriptions ha amarty, implied or otherwis ample or samples tested. mmended or altered. This dvertising providing the or lanaging Director of AWTA	we been provide se, as to the soun This document sh s document. The	d by the client unle se of the tested sam all not be reproduce tames AWTA Prod	iss otherwise st ples. The above i id except in full a uct Testing and	ated. AWTA est results rel nd shall be re AWTA Ltd m	Ltd makes no abe only to the indexed void if av be used in	

3001

Wach

MARLA JACKSON B.S. PICKI