



FIRE TEST REPORT INFORMATION

Classic Integra



Vantt 7500 Roll-up Aluminium Matting

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the NCC 2019 and Fire Resistance of Floor Coverings.

Class 2 – 9 Properties of Floor Material and Coverings

Specification C1.10 of the NCC 2019 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table 2; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification E1.5, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with Clause 6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Integra Vantt 7500 product, the fire test properties are:

- Critical Radiant Flux is 8.1 kW/m2
- Smoke Development Rate is 192 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our Product Data Sheets from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.





AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

TEST NUMBER : 7-586702-AV ISSUE DATE : 24/08/2012 PRINT DATE : 21/09/2012 ORDER NUMBER : 7048 ORDER NUMBER : 7048 CLIENT : CLASSIC ARCHITECTURAL PRODUCTS 6 BEAUFORT STREET PRESTON VIC 3072

SAMPLE DESCRIPTION Clients Ref: "Integra Ventt matting" Cut pile carpet adhered to aluminium frames Approximate pile height: 6mm

Material Specification: Nominal composition: 100% Polyamide 6.6 Nominal total pile mass: 950g/m2

Reaction to Fire Tests for Floorings Determination of the Burning Behaviour using a Radiant Heat Source ASISO 9239,1-2003

Date of sample arrival: 17/08/2012 Date tested: Results: 22/08/2012

CHF (Critical Heat Flux / Critical Radiant Flux)

1 2 3 Mean

7.8 8.3 8.1 8.1 kW/m2 8.1 Width kW/m2

Smoke Value

186 219

Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing

Observations: Melting

Each specimen was clamped to a substrate of δmm thick fibre reinforced cement board prior to testing.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use

196071 1 (END OF REPORT) PAGE 1

This Laboratory is accredited by the National Association of Testing Authorities, Australia, for
-Chemical Testing of Textiles & Related Products | Accreditation No. 983
-Mechanical Testing of Textiles & Related Products | Accreditation No. 985
-Heat & Temperature Measurement | Accreditation No. 1356

-Heat & temperature Measurement: is document is issued in accordance with NATA's accreditation requirements. Samples, an ntifying descriptions have been provided by the client unless otherwise stated. AWTA List ma-rantly, implied or otherwise, as to the source of the tested samples. The above test results relate only pipe or samples tested. This document shall not be reproduced except in full and shall be rendered mended or altered. This document, the names AWTA Product Testing and AWTA List may be vertising providing the content and format of the advertisement have been approved in advance naging Director of AWTA List.

3207

APPROVED SIGNATORY



Australian Wool Testing Authority Ltd.
Copyright - All Rights Reserved