

For Every Step

FIRE TEST REPORT INFORMATION

Classic Integra



Reversible R300 Aluminium Matting

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the <u>NCC 2019 and Fire Resistance of Floor Coverings</u>.

Class 2 – 9 Properties of Floor Material and Coverings

Specification C1.10 of the NCC 2019 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table 2; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification E1.5, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with Clause 6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Integra Verse R300 product, the fire test properties are:

- Critical Radiant Flux is 6.7 kW/m2
- Smoke Development Rate is 184 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our Product Data Sheets from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



For Every Step

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A,B,N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499							
		TEST REP	PORT				
Client : Classic Architectural Group Pty Ltd 2 Kiama Street Miranda NSW 2228				Test Number 15-002884 Issue Date : 24/07/2015 Print Date : 24/07/2015 Order Number : 370196			
Sample Description	Clients Ref : "Integra Rigid assembly of tufted Nominal Mass per Unit / Nominal Thickness :			ed aluminium		olors - Black,	Grey.
//SO 9239.1-2003	Reaction to Fire Tests f Radiant Heat Source	or Floorings. Do	ətərminati	on of the Bur	ning Behav	iour using a	
	Date of Sample Arrival 16/06/2015						
	Date Tested			23/07/2015			
	CHF Value		1	2	3	Mean	
	Length		6.6	6.8	6.8	6.7	kW/m²
	Width		8.2	52	2		kW/m²
	Smoke Value		1	2	3	Mean	
	Length Width		195 154	198	159	184	%.min %.min
	Melting Blistering					Mini No	mal
	The test results relate to conditions of the test, th hazard of the product in	ey are not intend			(6) CONTRACTOR OF CONTRACT	der the partic	
	Sample was conditioned relative humidity of 50±5	l in accordance w i% for a minimum	hith BSEN	13238:2001 a urs prior to tes	it a tempera ting.	ture of 23±2°	C and
	Each specimen was loos clamped prior to testing.	e laid on a substr	rate of 6mr	n thick fibre re	inforced cer	nent board, a	ind
30433 55	580					Page 1	of 1
Australizer Wool Lasting Authority Ltd. Copyright - All Rights Reserved	~	Accredited for compliance - Chamical Testing	with IBOVIEC 17		editation No.	963	n
		- Chamical Testing		: Acts	editation No.	963	63

0204/11/06

3201 APPROVED SIGNATORY

