



FIRE TEST REPORT INFORMATION

Classic Tredfx

A-138R

Aluminium Safety Stair Nosing for Surface Mount Applications

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the NCC 2019 and Fire Resistance of Floor Coverings.

Class 2 – 9 Properties of Floor Material and Coverings

Specification C1.10 of the NCC 2019 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table 2; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification E1.5, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with Clause 6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Tredfx A-138R product, the fire test properties are:

Critical Radiant Flux: 11.1 kW/m2Smoke Development Rate: 20 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our <u>Product Data Sheets</u> from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



For Every Step

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Classic Architectural Group Pty Ltd

2 Klama Street Miranda NSW 2228 Test Number :

15-002487

Issue Date : Print Date Order Number: 24/07/2015 24/07/2015 370196

Sample Description Clients Ref : "Tredfx low-profile gritted anti-slip stair nosing"

Aluminium base profile with silicon carbide gritted strip insert, colors - Black, Yellow

Nominal Mass per Unit Area/Density: Nominal Thickness: 1-2 mm

360g/lm

AS/ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 16/06/2015 Date Tested 23/07/2015 CHF Value 1 2 3 Mean Length 11.2 11.1 kW/m² 10.8 11.2 Width - kW/m² Smoke Value 2 3 Mean Length 19 19 22 20 Width 20 - %.min

Melting Minimal Yes Blistering

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior

5580

Page 1 of 1

30433



Samples and their liberalitying descriptions have been possibled by the client unless otherwise stated. AWTA Ltd makes no warranty, limplied or otherwise, as to the source of the tested samples. The above test results relate only to the semple or samples tested. This document shall not be negroduced except in full and shall be rendered votal if senseded or altered. This obcurrent, the narrans AWTA Product Testing and AWTA Ltd. way be used in alteralization producing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

3007

APPROVED SIGNATORY

0204/11/06