



SLIP REPORT INFORMATION

Classic Tredfx

BH10N

Solid Brass TGSI Individual Tactile

For your information regarding Slip Resistance Requirement for stairs and landings and ramps, the requirement for slip resistance of stairs and landings can be found in both Australian Standard AS4586, and HB 198:2014 'Guide to the specification and testing of slip resistance of pedestrian surfaces' Table 3A as follows:

"Stair treads and Stairway landings, and Ramps in buildings covered by NCC Volumes One and Two"

...Dry Stair tread, a stair non-skid nosing strip and a stairway landing; Ramps not steeper than 1:14 gradient (when dry) - The suggested minimum Wet Pendulum result is **Class P3**

...Wet Stair tread, a stair non-skid nosing strip and a stairway landing; Ramps not steeper than 1:14 gradient (when wet) - The suggested minimum Wet Pendulum result is **Class P4**

For further information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Slip Resistance, and covering off the details for the requirements of the NCC 2019 Building Code of Australia and AS 4586.2013 – Slip Resistance classification of new pedestrian surface materials.

For the Classic Tredfx BH10N product, the slip test properties are:

Reported SRV: 60

Class: P5

A copy of the Slip Test report is on the following page.

Please also feel free to download a copy of any of our Product Data Sheets from the website.

Please note Classic Architectural Group are not licensed Building Surveyors or DDA Consultants, nor do we in any way purport to be. We strongly recommend that you have this product and NCC requirements verified by an accredited party that it is fit for its intended application before installation, including its longevity.



For Every Step



4/40 Bessemer Street Blacktown NSW 2148 Phone 02 9621 3706 ABN 80 118 534 768

6 April 2016

Test Report No. R8677

Slip Resistance Classification of New Pedestrian Surface Materials AS 4586:2013 Appendix A (Wet Pendulum Test)

The slip resistance Classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface.

Requested by:

Tredfx / Classic Architectural

Client Address:

PO Box 126

Preston VIC 3072 Supplied by Classic Architectural

Product Manufacturer: Product Description:

Tredfx BH10 Brass Tactile Indicator, with grooved top

Test conducted according to:

AS 4586:2013 Appendix A

Location:

Slip Check Pty Ltd Test Facilities, Blacktown NSW 2148

Conducted by: Stuart Lumsden

Date:

8 March 2016

Temperature:

20°C

Sample: Rubber slider used: Unfixed

Cleaning: Conditioned: None

Slope of specimen:

Slider 96 Tested on a flat level surface Grade P 400 paper dry followed by wet lapping film

Direction of Test:

Perpendicular to upper surface

| | Specimen 1 | Specimen 2 | Specimen 3 | Specimen 4 | Specimen 5 |
|----------------------------|------------|------------|------------|------------|------------|
| Mean BPN of last 3 swings: | 61 | 59 | 59 | 58 | 63 |

| Reported SRV of Sample: | 60 |
|-------------------------|----|
| Class: | P5 |



Ryan Voorderhake

Laboratory/Field Technician