

For Every Step

FIRE TEST REPORT INFORMATION

Classic Tredfx



Polyurethane TGSI Directional Tactile Tile Format

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the <u>NCC 2019 and Fire Resistance of Floor Coverings</u>.

Class 2 – 9 Properties of Floor Material and Coverings

Specification C1.10 of the NCC 2019 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table 2; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with <u>Specification E1.5</u>, a maximum <u>smoke development rate</u> of 750 percent-minutes; and
- c) a <u>group number</u> complying with <u>Clause 6(b)</u>, for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Tredfx PT39A product, the fire test properties are:

- Critical Radiant Flux: 7.8 kW/m2
- Smoke Development Rate: 234 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our Product Data Sheets from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



For Every Step

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

		TEST	REPORT				
Client :	Classic Arch	nitectural Group Pty Ltd		Test	Number :	13-00243	6
	2 Kiama Street Miranda NSW 2228			Issue	Date :		1.0
				Print	Date :		
				Order	r Number :	37012	
Sample [Description	Clients Ref : *Polymer Tactile 100% Polyurethane ground surfa	Ground Surface I ce indicator, color		ow, Grey, Bei	ge	
		Nominal Mass per Unit Area/Dens Nominal Thickness : 5-6 mr		12			
-							-
S/ISO 9239.	1-2003	Reaction to Fire Tests for Floori	ngs. Determinati	on of the Bur	ning Behavio	our using a	
		Radiant Heat Source					
		Radiant Heat Source Date of Sample Arrival		21/05/2	1013		
				21/05/2 04/06/2			
		Date of Sample Arrival	1			Mean	
		Date of Sample Arrival Date Tested	1 8.7	04/06/2	013	Mean 7.8	kW/m
		Date of Sample Arrival Date Tested CHF Value		04/06/2 2	3		
		Date of Sample Arrival Date Tested CHF Value Length	8.7	04/06/2 2 7.0	2013 3 7.6		kW/m kW/m
		Date of Sample Arrival Date Tested CHF Value Length Width	8.7 9.1	04/06/2 2 7.0 -	3 7.5 -	7.8	
		Date of Sample Arrival Date Tested CHF Value Length Width Smoke Value	8.7 9.1 1	04/06/2 2 7.0 - 2	1013 3 7.6 3	7.8 - Mean	kW/m
		Date of Sample Arrival Date Tested CHF Value Length Width Smoke Value Length	8.7 9.1 1 243	04/06/2 2 7.0 - 2 258	1013 3 7.6 - 3 201	7.8 - Mean	kWin %.mi

conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using CA400 / butyl adhesive, and clamped prior to testing.

26139
5017
Page 1 of 1

 • Answering Authorny Lift Caryclyfic: All flights Reserved

 • Accordition for compliance with IBOREC 17025
 • Chemical Testing
 • Chemical
 • Ch