



FIRE TEST REPORT INFORMATION

Classic Integra

Zeal 8850

Dual Filament Carpet Style Matting

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the NCC 2019 and Fire Resistance of Floor Coverings.

Class 2 – 9 Properties of Floor Material and Coverings

Specification C1.10 of the NCC 2019 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table 2; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification E1.5, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with Clause 6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Integra Zeal 8850 product, the fire test properties are:

- Critical Radiant Flux is 1.8 kW/m2
- Smoke Development Rate is 470 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our Product Data Sheets from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



For Every Step

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A B N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

TEST NUMBER : 7-588313-CV ISSUE DATE : 04/12/2012 PRINT DATE : 05/12/2012 ORDER NUMBER : 7048 ORDER NUMBER : 7048 CLIENT : CLASSIC ARCHITECTURAL PRODUCTS PTY LTD 6 BEAUFORT STREET PRESTON VIC 3072 SAMPLE DESCRIPTION Clients Ref: "Integra Zeal 8850 Matting" Vinyl backed Matting Colour: Various Approximate Thickness: B.lmm Material Specification: Nominal Pile Composition: Nylon/Polypropylene Nominal Mass: 3500g/m2 Nominal Backing: Vinyl ASISO 9239.1-2003 Reaction to Fire Tests for Floorings
Determination of the Burning Behaviour
using a Radiant Heat Source
07/11/2012
Date tested: 29/11/2012
Results: CHF (Critical Heat Flux / Critical Radiant Flux)
1 2 3 Mean
Length 2.2 1.7 1.6 1.8
Width 2 . kW/m2 2.4 kW/m2 Smoke Value 471 412 526 Length 470 % min 456 Width % min Observations: Melting Blistering Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of $23 \pm \ell - 2\deg C$ and Relative Humidity of $50 \pm \ell - 5\%$ for a minimum of 48 hours prior to testing Each specimen was clamped to a substrate of $\hat{\boldsymbol{g}}$ mm thick fibre reinforced cement board prior to testing The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use 197384 1 (END OF REPORT) PAGE 1

This Laboratory is accredited by the National Association of Testing Authorities, Australia, for Chemical Testing of Testins & Related Products : Accreditation No. 983 - Machanical Testing of Testins & Related Products : Accreditation No. 985 - Machanical Testing of Testins & Related Products : Accreditation No. 985 - This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if anniended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

A JACKSON B So (Hone) NAGING DIRECTOR