

For Every Step

SLIP REPORT INFORMATION

Classic Tredfx

Concrete Paver - Warning

Integrated Concrete Paver Tactile

For your information regarding Slip Resistance Requirement for stairs and landings and ramps, the requirement for slip resistance of stairs and landings can be found in both Australian Standard AS4586, and HB 198:2014 'Guide to the specification and testing of slip resistance of pedestrian surfaces' Table 3A as follows:

"Stair treads and Stairway landings, and Ramps in buildings covered by NCC Volumes One and Two"

...Dry Stair tread, a stair non-skid nosing strip and a stairway landing; Ramps not steeper than 1:14 gradient (when dry) - The suggested minimum Wet Pendulum result is **Class P3**

...Wet Stair tread, a stair non-skid nosing strip and a stairway landing; Ramps not steeper than 1:14 gradient (when wet) - The suggested minimum Wet Pendulum result is **Class P4**

For further information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Slip Resistance, and covering off the details for the requirements of the NCC 2022 Building Code of Australia and AS 4586.2013 – Slip Resistance classification of new pedestrian surface materials.

For the Classic Tredfx Concrete Paver - Warning product, the slip test properties are:

Class: P5

A copy of the Slip Test is on the following page.

Please also feel free to download a copy of any of our Product Data Sheets from the website.

Please note Classic Architectural Group are not licensed Building Surveyors or DDA Consultants, nor do we in any way purport to be. We strongly recommend that you have this product and NCC requirements verified by an accredited party that it is fit for its intended application before installation, including its longevity.



For Every Step



Independent Slip Testing Services

+61 (0) 411 600 733

/+64 (0) 279 735 266 www.gpcsliptesting.com

TEST REPORT- Wet Pendulum Slip Resistance Classification (Australian Standard)

Report Prepared for:

Page #: 2 of 4 Program #: 8005

Test Date: 28-05-2024

Test Site: Independent Slip Testing Services-Slip Resistance Testing Facility (Lota Headquarters QLD Australia)

Testing Technician: G MacVitie

Testing Instrument: Pendulum Skid Tester with Slider 96 (45) rubber. Reported Uncertainty for testing device: 3.0 BPN

Testing Instrument W1- Serial #: SK1105

TESTING SPECIMEN DESCRIPTION, SIZE, COLOUR, TYPE, & COATING (if applicable)

1x Cautional Tactile Snow-T3, Bone, Tactile Paver, Sample Size 30x30cm

1x Cautional Tactile Snow- T3, Bone, Tactile Paver, Sample Size 30x30cm

1x Cautional Tactile Snow-T3, Bone, Tactile Paver, Sample Size 30x30cm

1x Cautional Tactile Snow- T3, Bone, Tactile Paver, Sample Size 30x30cm 1x Cautional Tactile Snow-T3, Bone, Tactile Paver, Sample Size 30x30cm

Surface Condition: Profiled Cleaning: Tested as received xed/ Unfixed: Unfixed Rz Mean: Air conditioning vironmental Conditions: 23 Deg.C Air Temp: irection of Test: As indicated on underside of sample Slope: n/a

AS 4586-2013

INTERPRETATION OF THE WET PENDULUM RESULTS		
Classification	Pendulum mean BPN Slider 96 (45) rubber	
P5	>54	
P4	45-54	
P3	35-44	
P2	25-34	
P1	12-24	
PO PO	<12	

TEST RESULTS (SRV)

#1 Result:	66 BPN	Slider condition (P400):	87 BPN
#2 Result:	66 BPN	Slider condition (Lapping):	60 BPN
#3 Result:	68 BPN	Temperature adjustment:	N/A
#4 Result:	64 BPN	Carpet surface tested dry:	N/A
#5 Result:	63 RPN		

CLASSIFICATION

CLASSIFICATION	SRV- PENDULUM MEAN BPN (Slider 96)
P5	65

The mean results of the five specimens is reported (rounded to nearest whole number)

* An individual result both below the result classification and below the mean result minus 20% shall be considered of lower classification

Maximum Slope Design Value (when dry):	12 deg
Maximum Slope Design Value (when wet):	6 deg

ANCC Code provides reference for ramps up to 1:8

ilac-MR/



Testing was carried out using the Wet Pendulum Test Method in accordance with Australian Standard AS 4586-2013 Appendix A