

For Every Step

FIRE TEST REPORT INFORMATION

Classic Tredfx



Aluminium Safety Stair Nosing for Surface Mount Applications

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the <u>NCC 2022 and Fire Resistance of Floor Coverings</u>.

Class 2 – 9 Specification 7 Fire Hazard Properties

S7C3 of the NCC 2022 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table S7C3; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification 17, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with S7C6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Tredfx DKR135 product, the fire test properties are:

- Critical Radiant Flux: ≥11 kW/m2
- Smoke Development Rate: 8 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our Product Data Sheets from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



For Every Step

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

Phone (03) 83/1 2400 Pax (03) 83/1 2489

		TEST	REPORT				
Client :	Classic Arch 2 Kiama Str Miranda NS			Issue I Print D		13-00243 05/06/20 05/06/201 37012	13
Sample	Description	Clients Ref : "Tredfx gritted ar Aluminium base profile with silico Nominal Mass per Unit Area/Dens Nominal Thickness : 5-6 m	sity : 960g/lm	rip insert, colo	rs - Black, Y	ellow, Grey	
S/ISO 9239	1-2003	Reaction to Fire Tests for Floorin Radiant Heat Source	ngs. Determinatio	on of the Burn	ing Behavio	our using a	
		Date of Sample Arrival			21/05/2013		
		Date Tested 04/06/2013					
		CHF Value	1	2	3	Mean	
		Length	≥11	≥11	≥11	≥11	kW/m³
		Length Width	≥11 ≥11	≥11 -	≥11 -	≥11 -	kW/m² kW/m²
		· .				≥11 - Mean	
		Width	≥11				
		Width Smoke Value	≥11 1	2	3		kW/m²
		Width Smoke Value Length	≥11 1 8	2	3		kW/m² %.min

conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

	26139	5017			Page 1 of 1
Ð	Assisten Waol keeling Authority Lid Copyright - All Rights Reserved		Accredited for compliance with ISCAEC 17025 C Parriade Tosting Mechanical Tosting Performance & Approvals Tosting Description and their Identifying descriptions have been provided by the client Id makes no variantly, implied or otherwise, as to the source of the tested relate only to the sample or samples tested. This document shall not be no be remoted visit if emerand or alterned. This document shall not be not be remoted visit if emerand or alterned. This document shall not be not be remoted visit if emerand or alterned. This document shall not be not be remoted visit if emerand or alterned. This document shall not be not the Managing Director of AWTA LM.	samples. The above test results roduced except in full and shall Product Testing and AWTA Ltd	
65	04/11/06		APPROVED SH	01 GNATORY	MECHANIEL A. JACKBON B.Bc.(Hons)