

For Every Step

FIRE TEST REPORT INFORMATION

Classic Tredfx

SBR103

Aluminium Safety Stair Nosing for Surface Mount Applications

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the NCC 2022 and Fire Resistance of Floor Coverings.

Class 2 - 9 Specification 7 Fire Hazard Properties

S7C3 of the NCC 2022 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table S7C3; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification 17, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with S7C6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Tredfx SBR103 product, the fire test properties are:

- Critical Radiant Flux: 7.8 kW/m2
- Smoke Development Rate: 234 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our <u>Product Data Sheets</u> from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



For Every Step

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

: 7-579085-CV : 10/06/2011 : 10/06/2011 CLASSIC ARCHITECTURAL PRODUCTS TEST NUMBER PTY LTD 6 BEAUFORT STREET PRESTON VIC 3072 PRINT DATE SAMPLE DESCRIPTION Clients Ref: "Stair Tread Nosing" PVC strips affixed to cement sheet Approx total thickness: 9.5mm End Use: Stair Nosing Material Specification: Nominal composition: PVC cement sheet Nominal mass: 3.5kg/m2 Reaction to Fire Tests for Floorings Determination of the Burning Behaviour using a Radiant Heat Source ASISO 9239.1-2003 Date of sample arrival: Date tested: Results: 24/05/2011 10/06/2011 CHF (Critical Heat Flux / Critical Radiant Flux) 2 3 Mean 7.6 7.0 Length Width 7.8 kW/m2 Smoke Value 201 243 254 Observations: transitory flaming, blistering, penetration of flame through to Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of $23+/-2\deg\mathbb{C}$ and Relative Humidity of 50+/-54 for a minimum of 48 hours prior to testing Each specimen was clamped as supplied by client prior to testing The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use (END OF REPORT) PAGE 1 188107 1

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

This Laboratory is accredited by the National Association of Testing Authorities, Australia, for Chemical Testing of Testiles & Related Products : Accreditation No. 983 Machanical Testing of Testiles & Related Products : Accreditation No. 983 Hachanical Testing of Testiles & Related Products : Accreditation No. 1366 Heat & Temperature Measurement : Accreditation Ro. 1366 Heat & Temperature Measurement is issued in accordance with NATA's accreditation requirements. Samples, and 56er identificantlying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warrarity, implied or otherwise, as to the source of the tested samples. The above test results relate only the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

HARLA JACKSON B.So.(Hork)