

For Every Step

FIRE TEST REPORT INFORMATION

Classic Tredfx

SH60N

Stainless Steel TGSI with Grit Insert

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the NCC 2022 and Fire Resistance of Floor Coverings.

Class 2 - 9 Specification 7 Fire Hazard Properties

S7C3 of the NCC 2022 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table S7C3; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification 17, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with S7C6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Tredfx SH60N product, the fire test properties are:

Critical Radiant Flux: 11.3 kW/m2Smoke Development Rate: 2 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our <u>Product Data Sheets</u> from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



For Every Step

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Classic Architectural Group Pty Ltd

> 2 Kiama Street Miranda NSW 2228

Test Number :

13-002437

Issue Date Print Date

05/06/2013 05/06/2013

Mean

Mean

1

11.3 kW/m²

kW/m²

2 %.min

- %.min

Order Number:

37013

Sample Description

Clients Ref:

Length

Width

"SH60 Tactile Ground Surface Indicator

Stainless Steel body with silicon carbide infil colors - Black, Yellow.

Nominal Mass per Unit Area/Density:

8500g/m2 (400 pieces per m2)

Nominal Thickness: 4-5 mm

AS/ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 21/05/2013 Date Tested 04/06/2013 CHF Value 1 2 3 Length 11.7 11.0 11.2 Width 11.1 Smoke Value 2 1 3

Melting Slight Blistering

2

2

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using lits own rear stem, and clamped prior to testing.

26139

5017

Page 1 of 1

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



may be used in advertising providing the content and for the Managing Director of AWTA Ltd.

2007

APPROVED SIGNATORY