

**For Every Step** 

### FIRE TEST REPORT INFORMATION

#### Classic Tredfx

# **GENERAL PURPOSE TAPE - Black**

Anti-slip Self-adhesive Tape

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the NCC 2022 and Fire Resistance of Floor Coverings.

#### Class 2 - 9 Specification 7 Fire Hazard Properties

S7C3 of the NCC 2022 states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table S7C3; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification 17, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with S7C6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the Classic Tredfx General Purpose Tape (Black) product, the fire test properties are:

Critical Radiant Flux: 10.8 kW/m2

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our <u>Product Data Sheets</u> from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.





# **3M** Safety-Walk<sup>™</sup> General Purpose

## **Product Bulletin**

#### Description:

The product consists of abrasive particles bonded by a tough, durable polymer to a dimensionally stable plastic film. The reverse side is coated with a rubber based pressure sensitive adhesive, covered by a removable protective liner. The product provides a durable, slip resistant surface for a large variety of applications.

#### **Product Positioning:**

Primarily for use as a durable, slip resistant surface for dry, wet, oily floors in industrial and commercial applications with intensive pedestrian or light vehicle traffic such as: corridors, production and storage rooms, ramps, stairways, ladders, footplates on machines, emergency exits ...

#### Product Advantages:

- · Safe, slip resistant surface
- Strong and very durable
- Resistant to chemicals
- Easy to install
- Excellent bond to most dry, clean, smooth surfaces

#### Colours:

•	Black	#610
•	Clear	#620
•	Yellow	#630

#### Standard Sizes:

#### Rolls:

25 mm x 18.2 m 51 mm x 18.2 m 100mm x 18.2 m 150mm x 18.2 m 300mm x 18.2 m 600mm x 18.2 m 914mm x 18.2 m

#### Product requirements:

Property Test method	Value		
Colour:	Black	Other	
Applied thickness ★:	0.76	1.02	
<ul> <li>MIL D-17951 Ships</li> </ul>	mm	mm	
Applied weight ★:	560	710	
<ul> <li>MIL D-17951 Ships</li> </ul>	g/m <sup>2</sup>	g/m <sup>2</sup>	
Resistance to U.V:	Good		

Property Test method	Value	
Flammability: IMO A.653 (16) Ships F16101 (trains) ASTM E 648-95a Average critical radiant flux (W/cm²): NFPA 101: GSA classification: Bureau Veritas (Fr): C.A.A approval: FAR 25853-B	Passes M2F1 >1.08 Type I Class A Class 0 Yes Passes SF 3	>1.05 Type I Class A
DIN 5510 (Ge): Smoke Density and Toxicity:     IMO MSC 61-(67)     Annex 1, Part 2. Smoke Density (Dm corrected):     ASTM E622-94a Flaming	Passes	83
Non-Flaming Minimum application temperature: Minimum service temperature: Maximum service temperature:	84 90 4°C / 40°F Minus 40°C Minus 40°F 79°C / 175°F	

Issued August 2005
January 2003
Author: George Di Scala Page 1 of 4

Author: George Di Scala Page 1 of 4							
Dynamic co	efficient of						
friction							
MIL-D-17951 Ships							
Surface	Condition	Values					
Rubber	Dry	1.24	1	.12			
	Water	1.20	0	.92			
	Oil	0.80	0	.59			
Leather	Dry	0.93	0	.83			
	Water	1.14	0.89				
	Oil	N/A	N	I/A			
	Static coefficient of						
friction:							
<ul> <li>MIL-D-17951 Ships</li> </ul>							
Surface	Condition	Values					
Rubber	Dry	1.32	1.27				
	Water	1.29	1.09				
	Oil	0.98	0	.77			
Leather	Dry	1.12	1.11				
	Water	1.45	1.11				
	Oil	N/A	N	I/A			
Slip resistance:							
<ul> <li>DIN 51130 (ZH1/571)</li> </ul>							
<ul> <li>AS 4586:1999</li> </ul>			*	•			
<ul> <li>AS 4586:</li> </ul>							
<ul> <li>AS 4586:</li> <li>Friction (d)</li> </ul>		13	12	11			
	ry) R=	13	12 4	-			

- \* Typical average values
- Values for clear
   Value for yellow





3M Australia PTY LTD . A.C.N. 90 000 100 096 Commercial Care & Food Services Laboratory 25-27 Bridge Street PYMBLE NSW 2073

Phone 02 9498 9461Customer Service 136 136