



classic
architectural group



For Every Step

FIRE TEST REPORT INFORMATION

Classic Tredfx

GRIT TAPE- Standard

Anti-slip Self-adhesive Tape

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the [NCC 2022 and Fire Resistance of Floor Coverings](#).

Class 2 – 9 Specification 7 Fire Hazard Properties

[S7C3 of the NCC 2022](#) states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table S7C3; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification 17, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with S7C6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the **Classic Tredfx Grit Tape (standard)** product, the fire test properties are:

- Critical Radiant Flux: 11.1 kW/m²
- Smoke Development Rate: 20 %/min


A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our [Product Data Sheets](#) from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



classic
architectural group



For Every Step



TEST REPORT No. 125787

LABORATORY REF: P125787

CUSTOMER REFERENCE

ANTI SLIP TAPE " HT25B/SY "

Sample description as provided by customer
#35 GRIT CARBORUNDUM ANTI-SLIP TAPE

TEST METHOD AS/ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by specification C1.10a of the Building Code of Australia.

The test values relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product. Clause 9 of AS/ISO 9239 Part 1.

Conditioning as specified in BS EN 13238.2001

Sample submitted Date August 2012

Test Date 04 Sep 2012

ASSEMBLY SYSTEM: DIRECT STICK Self Adhesive.

The floor covering was directly stuck to the substrate using Self Adhesive adhesive.

Substrate: Non-Combustible

Substrate - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.

The Holding Torque on Specimen Frame was 2Nm.

Initial Test Specimen 1 Length Direction Critical Radiant Flux 11.3 kW/m²
Specimen 1 Width Direction Critical Radiant Flux 11.2 kW/m²
Full tests carried out in the Width Direction

SPECIMEN	Width #1	Width #2	Width #3	Mean
Critical Radiant Flux (kW/m ²)	11.2	10.8	11.2	11.1
Smoke Development Rate (%.min)	19	19	22	20

The values quoted below are as required by Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia. The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).

MEAN CRITICAL RADIANT FLUX 11.1 kW/m²

MEAN SMOKE DEVELOPMENT RATE 20 percent-minutes


OBSERVATIONS: The samples shrunk away from the heat source, ignited and burnt a extremely short distance.



M. B. Webb
Technical Manager

DATE: 04 Sep 2012

Measurement Science & Technology No. 15393
Accredited for compliance with ISO/IEC 17025.



PAGE 1 of 2

This Page (1) has been designed to show the values required under Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia.

The values on Page 2 have no relevance to the Code.

1004 04 09

APL Australia Pty Ltd
5 Cannish Rd. Oakleigh South
Victoria 3167 Australia

Telephone: 03 9543 1618
Facsimile: 03 9562 1818
Mobile: 0411 039 088

Email: apl@aplaustralia.com.au
Web: www.aplaustralia.com.au
ABN 69 468 849 319

