



classic
architectural group



For Every Step

FIRE TEST REPORT INFORMATION

Classic Integra

Zeal 8850

Dual Filament Carpet Style Matting

For your information, please also find a link to our 'White Paper' containing some explanatory information pertaining to Fire Resistance, and covering off the details for the requirements of the [NCC 2022 and Fire Resistance of Floor Coverings](#).

Class 2 – 9 Specification 7 Fire Hazard Properties

[S7C3 of the NCC 2022](#) states that a floor lining or floor covering must have:

- a) a Critical Radiant Flux (CRF) not less than that listed in the Table S7C3; and
- b) in a building not protected by a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification 17, a maximum smoke development rate of 750 percent-minutes; and
- c) a group number complying with S7C6(b), for any portion of the floor covering that is continued more than 150 mm up a wall.

For the **Classic Integra Zeal 8850** product, the fire test properties are:

- Critical Radiant Flux is 1.8 kW/m²
- Smoke Development Rate is 470 %/min.

A copy of the Fire Test report is on the following page.

Please also feel free to download a copy of any of our [Product Data Sheets](#) from the website.

Please note Classic Architectural Group are not licensed Building Surveyors, nor do we in any way purport to be. We strongly recommend that you have this product verified by an accredited party that it is fit for its intended application before installation.



classic
architectural group

For Every Step

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : CLASSIC ARCHITECTURAL PRODUCTS PTY LTD
6 BEAUFORT STREET
PRESTON VIC 3072

TEST NUMBER : 7-588313-CV
ISSUE DATE : 04/12/2012
PRINT DATE : 05/12/2012
ORDER NUMBER : 7048
ORDER NUMBER : 7048

SAMPLE DESCRIPTION Clients Ref: "Integra Zeal 8850 Matting"
Vinyl backed Matting
Colour: Various
Approximate Thickness: 8.1mm

Material Specification:
Nominal Pile Composition: Nylon/Polypropylene
Nominal Mass: 3500g/m²
Nominal Backing: Vinyl

ASISO 9239.1-2003 Part 1 Reaction to Fire Tests for Floorings
Determination of the Burning Behaviour
using a Radiant Heat Source

Date of sample arrival: 07/11/2012
Date tested: 29/11/2012

	CHF (Critical Heat Flux / Critical Radiant Flux)				
	1	2	3	Mean	
Length	2.2	1.7	1.6	1.8	kW/m ²
Width	2.4	-	-	-	kW/m ²
			Smoke Value		
Length	412	526	471	470	% min
Width	456	-	-	-	% min

Observations: Melting
Blistering

Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use

197384

1

(END OF REPORT)

PAGE 1

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
-Chemical Testing of Textiles & Related Products : Accreditation No. 983
-Mechanical Testing of Textiles & Related Products : Accreditation No. 985
-Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

020411/06